

An experimental investigation on splicing of reinforcement in reinforced concrete beam by bar coupler

#1.G.Raju,*2 Mrs. K. Selvi., M.E.,

PG Scholar, *Associate professor

Department of Civil Engineering

Nandha Engineering College (Autonomous), Erode.

E-Mail: raj.jaycivil@gmail.com

Abstract: Reinforced cement concrete is the concrete with certain percentage of steel reinforcement embedded in it. This reinforcement is provided mainly to take care of the tensile stresses developed in the member. Reinforcement also limits the size of cracks in concrete due to shrinkage and temperature variation. Splicing of reinforcement bars in R.C members since the manufacturing length of reinforcement bar is 12m only in the market does not suit always to the exact dimensions of the members. The common types of splices adopted are lap splice and welded splice. The lapped joints are not always an appropriate means of connecting reinforcing bars. The use of laps can be time consuming in terms of design and installation and can lead to greater congestion within the R.C member because of the increased amount of rebar used. The cost of reinforcement also increased. The cost of reinforcement can be reduced and increase the load carrying capacity of RCC beam by using coupler to join the end of reinforcement. The investigation reported in this paper was carried out the behavior of splicing of reinforcement by bar coupler in beam. Test the flexural strength of M25 grade coupler reinforced concrete beam. The mix proportions of M25 grade concrete are designed by using Indian standard method and Fe 415 grade steels are used. Two numbers of RC beams casted (conventional lap and coupler reinforcement) for flexural strength test. The results showed that comparison of the flexural strength of conventional lap RC beam and coupler reinforced beam and analysis of cost of reinforcement. Comparison between conventional RC beam and bar coupler used RC beam. Tensile strength of coupler used reinforcement bar. Ultimate load carrying capacity of conventional RC beam. Ultimate load carrying capacity of

bar coupler used RC beam. Are analyzed in phase-II project work.

Keywords: zero-droop, low stacking force, contamination.

I. INTRODUCTION

General: Reinforcement is a general term used in RCC Structures Standard and by designer, reinforcement processors and building contractors. Steel bars includes deformed bars, plain bars, wire, fabric and steel products, all of which increase the tensile and compressive stress carrying properties of concrete. Steel reinforcement is also the essential contributor towards crack control of concrete structures.

Concrete is very good in compression but weak in tension. Various members in structure are always subjected to tensile forces, bending forces etc. To take these factors and to transfer them safely to other members, the structural members are always reinforced with steel reinforcement bars.

There are four common types of reinforcing bars.

- Mild steel bars
- Cold twisted deformed bars (C.T.D)

- High yield strength deformed bars (H.Y.S.D)
- Thermo mechanical treated steel bars(TMT)

In building construction C.T.D/HYSD/TMT bars are used as primary reinforcement i.e. main steel and mild steel bars are used as secondary reinforcement such as ties, stirrups and distribution steel. Generally mild steel of 6mm diameter is used as secondary reinforcement and deformed bars of diameter 8, 10, 12, 16, 20, 25, 32 & 40 mm used as main reinforcement.

Reinforcement shall have concrete cover and the thickness of such cover shall be as follows

- At each end of reinforcing bar not less than 25mm or twice of such bar diameter whichever is greater.
- For longitudinal reinforcing bar in a beam not less than 25 mm
- Footings : 50 mm
- Raft foundation Top : 50 mm
- Raft foundation Bottom/ sides : 75 mm
- Strap Beam : 50 mm
- Grade Slab : 20 mm
- Column : 40 mm (d>12mm) 25 mm (d=12mm)
- Shear Wall : 25 mm
- Beams : 25 mm
- Slabs: 15 mm or not less than diameter of the bar.
- Flat Slab : 20 mm
- Staircase : 15 mm
- Retaining Wall on Earth : 20/ 25 mm
- Water retaining structures : 20 / 30 mm

- Sunshade (Chajja) : 25 mm
- Hook for stirrups is 9D for one side
- No. of stirrups = (clear span/Spanning) + 1

II. MATERIALS USED

Cement - Ordinary Portland cement of review 53 is utilized as a part of the pervious cement and the concrete is utilized as a coupling material.

Coarse aggregate - Locally accessible pulverized blue rock stones adjusting to reviewed total of ostensible size 12.5 mm according to Seems to be: 383 – 1970. Smashed rock total with particular gravity of 2.77 and going through 4.75 mm strainer and will be utilized for throwing all examples. A few examinations infer that most extreme size of coarse total ought to be confined in quality of the composite. Notwithstanding bond glue – total proportion, total sort impacts concrete dimensional dependability.

Water - Water utilized for blending ought to be compact drinking water having pH values between 6 to 8 and it ought to be free from natural matters and the strong substance ought to be inside as far as possible according to IS 456-2000 and fitting in with IS 3025-1964. In the present test concentrate the water accessible inside the school grounds is utilized for all reasons.

Fine aggregate-Naturally available fine aggregate is used for casting the beam specimens. The fine aggregate was passing through 4.75 mm sieve with grading as per Indian standard specification (IS 383:1997) was used.

The most commonly used fine aggregate is the river sand. It passes through 4.75mm sieve.

The three types of sand are,

- River Sand
- Pit sand
- Sea Sand

Sand covers the major part of the construction forum. Until the introduction of fly ash and quarry dust river sand was the only fine aggregate to be used. In Tamil Nadu the most common places where river sands are collected are Trichy and karur.

Reinforcement - Thermo mechanical treated reinforced steel bars (TMT) is used for longitudinal

main reinforcement with 16 mm diameter. For shear reinforcement 6 mm diameter two legged stirrups were used with a spacing of 100 mm c/c. Thread is formed at end of the reinforcement with 20 mm length for each bars. The properties of reinforcement is tabulated in table.1

Properties of reinforcement:

Sl	properties	description
1	Yield strength	415 N/mm ²
2	Grade	Fe 415
3	Type	TMT
4	Carbon content	0.55 to 1.5%
5	Thermal resistance	Up to 600°C
6	Minimum % of elongation at failure	14.5%

Reinforcement bar couplers: Lapped joints are not always an appropriate means of connecting reinforcing bars. The use of laps can be time consuming in terms of design and installation and can lead to greater congestion within the concrete because of the increased amount of rebar used.

Available to suit bar sizes 12mm to 50mm, the couplers are installed quickly and easily on site without the need for specially trained personnel or specialized, expensive machinery.

The length of reinforcement bar coupler is 70 mm used to connect two main longitudinal bars. The external diameter of coupler is 25 mm are used.



Bar coupler

Dimensions of the couplers required for different diameter of bars are tabulated in table.2

Table .2 Dimensions of couplers

Bar diameter (mm)	12	16	20	25	28	32
External	21	26	32	40	45	50

diameter						
Coupler length	32	40	48	60	66	72
Weight (kg)	0.04	0.09	0.16	0.32	0.43	0.58

Thread coupler is designed to meet the requirements of BS 8110 and to achieve failure loads in excess of 115% of the characteristic strength of grade 500 rebar. A nominal allowance of +25mm should be allowed per threaded bar end.

The couplers are generally torque onto the reinforcing bar in the bar threading shop, the internal threads protected by plastic end caps. The threaded ends of the continuation bar are protected by plastic thread protectors.

III. MIX PROPORTION

Based on IS Method:

Target strength	= 25Mpa
Max size of aggregate used	=12.5mm
Specific gravity of cement	= 3.11
Specific gravity of fine aggregate (F.A)	= 2.6
Specific gravity of Coarse aggregate (C.A)	= 2.80
Dry Rodded Bulk Density of (F.A)	=1726Kg/m ³
Dry Rodded Bulk Density of (C.A)	= 1638 Kg/m ³

Design mix proportions:

Water	cement	Fine aggregate	Coarse aggregate
191.6litr	445Kg/m ³	529.1 Kg/m ³	1106.84/m ³
0.48	1	1.1	2.48

Cement : Fine agg (kg/m³) : Coarse agg (kg/m³) :
Water (l/m³) : Super plasticizer (l/m³)

(1: 1.1 :2.48 :0.29 :0.8)

IV. EXPERIMENTAL ANALYSIS

A. Tensile strength test of steel bar



Observation:

Diameter of rod (M.S) d	= 16 mm
Gauge Length (L ₄)	= 300 mm
Gauge Length of Extensometer	= 330 mm
Least Count of Extensometer	= 0.01mm
Ultimate load	= 83.5 KN
Area	= $(\pi / 4) \times d^2$ = $(\pi/4) \times 16^2$ = 201.06 mm ²

Calculation:

Ultimate Stress	= ultimate Load /Area
	= $(83.5 \times 1000) / (201.06)$
	= 415.29 N/mm ²

Bar coupler:

Couplers has been tested and approved by UK CARES to show compliance with the requirements of BS 8110. The most common sizes have been tested and approved by the DIBt and are Covered by Approval No Z-1.5-179. "Mechanical Steel Reinforcement Couplers" and have been awarded KOMO Certificate No. K23495/02.



V. COUPLER SPECIFICATION

Ancon Couplers can be specified using the part numbers which are included in the tabulated data in each section of this brochure. The following examples show how each type of coupler should be specified when using 20mm bar.

Typical coupler specification:

Type of coupler	Reference
Tapered Thread Standard	TTS20
Tapered Thread Positional	TTP20
Tapered Thread Transition	TTT20
Tapered Thread Starter Bar	TTSB20
Tapered Thread Weldable	TTW20
Bartec Type A	BT20/A
Bartec Type B	BT20/B
Bartec Type C	BT20/C
Bar X-L Type A	XL20/A
Bar X-L Type B	XL20/B
Bar X-L Type C	XL20/C
MBT ET Series	ET20

VI. COST ANALYSIS

Dia Of Bar	Length (Ld) In meter	No of splicing	Cost per Bar coupler	Total Cost per Beam
Column 16 mm	0	4	35.00	140
Beam 16 mm	0	4	35.00	140
Column 20 mm	0	4	40.00	160
Beam 20mm	0	4	40.00	160

Cost Of Bar Coupler Reinforcement Beam:

V. CONCLUSION

The mix proportion of M25 grade concrete. Dimensions of couplers are determined. The length of coupler is 40mm, external diameter of coupler is 26 mm, and weight of coupler is 0.09 kg. Tensile strength of TMT reinforced bar is tested by using UTM machine the tensile strength is 415 N/mm². Thermo mechanical treated reinforced steel bars (TMT) is used for longitudinal main reinforcement with 16 mm diameter. The length of the thread at reinforcement end is 20 mm.

Conclusions based on the cost analysis:

Based on the cost analysis between over lapping reinforcement beam and bar coupler used reinforcement beam, the following conclusions were made.

- When bar couplers used in RC column for splicing, we can reduce the cost up to 40 % in column.
- When bar couplers used in RC beam for splicing, we can reduce the cost up to 51.3 % in beam.
- The development length of the beam and column is reduced.

Scope for Future Work:

- This project suggests many recommendations for future research.

- Different clear cover dimensions are suggested to be used. The cover used is based on protecting steel from corrosion.
- Corrosion resistant bar coupler may use for splicing of reinforcement.
- The flexural strength and deflection determine and compare between welded reinforcement and bar coupler used reinforcement beam.
- Bar coupler may be used in structural elements like Girders and columns, should be carried out in future.
- The flexural strength of beam may determine by different grade of concrete by design mix.
- Different bar coupler may be used in future work.

VI. REFERENCE

- M. K. Thompson, J. O. Jirsa, J. E. Breen, and R. E. Klingner "Anchorage Behavior of Headed Reinforcement" in May 2002.
- Reinforcement hand book of The Australian Steel Company (Operations) Pty Ltd . Fifth Edition 2008.
- IS: 1852 – 1985 Indian standard specification for rolling and cutting tolerances for hot-rolled steel product (fourth revision).
- IS : 5525 – 1969 indian standard recommendations for detailing of reinforcement in reinforced concrete works.
- ANCON Reinforcing Bar Couplers Construction industry. BS4449: 1997.
- University of Kansas Structural Engineering and Materials Laboratory report 2015. Mechanical coupler testing report.
- R.I. Gilbert "Detailing of Reinforcement in Concrete Structures" 28 August 2012.
- Keith L. Coogler Kent A. Harries, Ph.D., P.Eng. Marcy Gallick, P.E "Evaluation of Offset Mechanical Reinforcing Bar Splice Systems" in December 2006
- C. Paulson and J.M. Hanson Wiss, Janney, Elstner Associates, Inc. Chicago and Northbrook, Illinois "Fatigue behavior of welded and mechanical splices in reinforcing steel"
- Departmental Material Specifications DMS-4510 "Mechanical Couplers for Reinforcing Steel" January 2005–June 2009.